

TECHNICAL DATA SHEET NO: HEAT VERSION: 27.11.2009
PAGE: 1 of 3 PRINT DATE: 9/12/2014

EVERFLEX HEATMATE SILICONE



Colour	Product Code	Pack Size	Box Qty
Red	HEAT	C3	12
Black	HTSBK	C3	12

Product Description

EVERFLEX HEATMATE SILICONE is a high modulus, reactive curing silicone sealant specifically designed for high temperature applications. HEATMATE cures quickly to reduce dirt pick up. It remains permanently flexible, forming a weathertight rubber-like seal.

Benefits

- Excellent temperature resistance: remains flexible from -50 +300°C
- Extremely low dirt pick up. 1 hour tack free.
- Orange/red colour for easy installation identification.
- Excellent adhesion to non-porous surfaces.
- Waterproof seal

Areas For Use

- Multitude of Industrial uses
- As a gasket sealant.
- For joints and assemblies, which must be resistant to high temperatures in ducting, metal chimneys, industrial/domestic ovens, heating appliances.

Limitations

- Do not use on porous surfaces such as brick, concrete and stone.
- Do not use in conjunction with bitumen, lead or Asphalt.
- Not for use on substrates that may bleed oils, solvent or plasticisers.
- Do not use on soft metals such as lead or brass.
- On temperatures above 285°C, slight discolouration may occur, but the joint will maintain its integrity.
- Do not use above 300°C.

Surface Preparation

All surfaces must be clean, dry and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application. Highly porous substrates such as new plaster should first be primed with a dilution of Caulk with water at a ratio of 1:2. Can be applied to slightly damp surfaces.



TECHNICAL DATA SHEET NO: HEAT VERSION: 27.11.2009
PAGE: 2 of 3 PRINT DATE: 9/12/2014

Application

The surfaces to be must be clean, dry and free from dust, grease and other contaminants. Improve adhesion by wiping surface with white spirits. Priming is generally not required, although we always advise testing small areas prior to use.

Joint design should be as follows:

Minimum width: 6mm. Movement capacity will be impaired if the depth of the joint is greater than the width. For maximum movement accommodation, it is recommended that:

- 1. The joint depth should be no less than 5mm
- 2. Joint depth should be 5mm for joints up to 10mm wide
- 3. Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints

Triangular fillets should be no less than 12mm across the face and should be finished with a flat or convex face.

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the trigger and keeping the gun at a constant angle to the surface being sealed. To ensure a proper bond, always smooth the sealant down with a spatula or piece of wood wetted with linseed oil or white spirits. An improved joint appearance can be achieved by placing masking tape to both sides of the joint, removing within 5 minutes of application

Specific Data

Specific Data		
Movement Accommodation	+ or – 20%	
Skinning Time	5 mins @ 20°C	
Cure Time	3mm per 24 hours	
Hardness Shore A	23	
Shrinkage	<5%	
Service Temperature	-50 to +300°C	
Resistance		
Application Temperature	+ 5 to 40°C	
Tensile Strength	1.0 Mpa	
Stress	0.3 Mpa	
Specific Gravity	1.04	
Cleaning	Uncured sealant: white spirit	
	Cured sealant: Silicone Eater	
Minimum Joint Width	6mm	
Maximum Joint Width	30mm	
Joint Ratio	Maximum depth 50% of joint width	
Coverage	@ 10 linear metres 9 x 9mm fillet joint	

Health & Safety

Consult MSDS for full list of hazards

Storage

Store in cool dry conditions between + 5'C and 25'C.



TECHNICAL DATA SHEET NO: HEAT VERSION: 27.11.2009
PAGE: 3 of 3 PRINT DATE: 9/12/2014

Shelf Life

24 months from date of manufacture.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.