

RESIBLOCK *INDIAN SANDSTONE*

HEHE

surface

S

RESIBLOCK

Quattro

.....

SEALER INVISIBLE

Virtually undetectable following

application
Polymerisation
effected by
atmospheric
and residual
moisture

Can be applied
all year round
(see application
information).

Allows
pavement to
retain its
normal flexural
qualities

Manufactured
under ISO 9002

Easy
application by
Resiblock
application
roller or brush
High degree of
resistance to
chemicals.

PRODUCT DESCRIPT ION

RESIBLOCK INDIAN SANDSTONE

*SEALER
INVISIBLE is a
low viscosity
sealer which is
virtually
undetectable
following
application. The
deep penetrating
formulation
penetrates dry
porous surfaces to
form a membrane
in protecting
against dirt
detritus and fluid
penetration
damage. Its
unique
formulation is
both UV resistant
and will provide
long lasting
protection against
dirt detritus and
fluids even after
the initial beading
has gone.*

THE SYSTEM

Ideal for use with:- Indian Sandstone
Sandstone
Yorkstone
Limestone
And other forms of Natural Stone

Limitations of Use PIC, Engineering Bricks, Quarry Tiles
marble and slate

FEATURES

Resistant
staining by dirt
detritus and
fluids

GENERAL TECHNICAL DATA

Coverage

4 -6m² per litre

Cleaning of Tools

RESICLEAN

Drying Times 2 hrs @ 20° C

Storage

Store under cover and protect from extremes of temperature.
Ensure contents of container are thoroughly mixed.

Flash Point 44° C

Can Sizes

5 litre

Shelf Life

18 months (unopened containers)

Shipping Specification Packing Group III

UN No. 1263 – Class 3

RESIBLOCK *INDIAN SANDSTONE SEALER* *INVISIBLE*

APPLICATION INFORMATION

- 1 Make sure the surface and **jointing sand** are THOROUGHLY DRY and free from dirt.
- 2 Ensure that RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is only applied when there is no risk of rain within the next 8 hours.
- 3 Do not apply in extremes of temperature (below 3° C or above 30° C). For temperatures above this range contact our application dept for special procedures.
- 4 Ensure paving is thoroughly swept and that where applicable no jointing sand remains in the chamfers of the pavers.

5 Apply to surface using a Resiblock application roller, remove any build up in depressions with a clean roller or builders sponge.

6 Application rates vary depending on porosity but will be in the order of 4-6m² per litre. Where the paving has a sand filled joint (nominal 5mm) material usage should be increased to 2-3m² per litre.

7 Avoid walking on the sealed area for 3 hours after application and do not drive motor vehicles on the surface for 24 hours.

8 RESIBLOCK Indian Sandstone Sealer Invisible is NOT a sand stabiliser.

9 ALWAYS WEAR PROTECTIVE GLOVES AND GOGGLES. NO SMOKING. WEAR A MASK WHEN WORKING IN CONFINED AREAS. Please refer to current MSDS.

10 All uncured sealant and tools should be cleaned immediately using RESICLEAN.

HEALTH & SAFETY

PVC gloves and protective clothing/face shield must be worn, plus use of a barrier cream on exposed areas of skin, as uncured RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* may be considered a hazardous material.

No smoking or naked flames to be allowed, as RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is FLAMMABLE. Ensure area to be treated is well ventilated. If public access is allowed, erect NO SMOKING signs and site fire extinguishers

A mask of the recommended type is **essential** when using a paintbrush, working close to the surface or internally. Sabre or Martindale is recommended.

Do not apply RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* in the presence of foodstuffs. Once fully cured RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* can be considered innocuous. Do not clean hands with RESICLEAN as solvents may de-fat skin leading to dermatological problems.

Do not return unused material to original containers. DO NOT RESEAL or store partly used kegs. Material so stored may have poor adhesion, Carbon Dioxide may generate and put the drum under pressure, which

might rupture the drum. Furthermore partial or total solidification of the sealant may occur.

PLEASE NOTE THIS DATA SHEET REPRESENTS AN ABBREVIATION ONLY OF TECHNICAL INFORMATION,

PARTICULARLY AS IT RELATES TO FIELDS OF USE, APPLICATION AND HEALTH AND SAFETY. AS SUCH IT IS ESSENTIAL THAT THE LATEST COPY OF OUR FULL TECHNICAL DATA IS CONSULTED

The logo for Resiblock, featuring the word "RESIBLOCK" in a bold, serif font, enclosed within a rectangular border with a double-line effect.

RESIBLOCK

Resiblock Ltd, Resiblock House, Archers Fields Close, Basildon, Essex SS13 1DW United Kingdom Telephone: +44 (0)1268 273344 Fax: +44 (0)1268 273355 email: technical@resiblock.com www.resiblock.com